

MANUAL SECTION	ISSUE DATE	AUTHORISED	REPLACES	PAGE
<i>Exteriors</i>	<i>August 2005</i>	<i>PM</i>	<i>Sept 1999</i>	<i>I of 2</i>

FLEXIGLAZE

GENERIC TYPE:

Pure acrylic coating.

TYPICAL PROPERTIES:

- FLEXIGLAZE is a pure acrylic, elastomeric pigmented (coloured) glaze coating for exterior wall application.
- Can be applied as a smooth finish, or over textures.
- Good flexibility.
- Good weatherproofing properties.
- Non-flammable.
- Non-toxic.
- Low odour.
- Total solids content: 50%
- Volume solids: 40%
- S.G.: 1.2kg/litre
- Finish: Gloss, semi-gloss, low sheen
- Early Fire Hazard:

Ignitability	0
Spread of Flame	0
Heat Evolved	0
Smoke Developed	4

Colour:

- White, plus a selection of colours
- Special colours to order
- Choose from BS5252 colour charts
- Any colour may be matched

SUGGESTED USES:

Coating of commercial and residential building exteriors (both new and existing) of concrete plaster, brick, concrete blocks, fibre cement sheets, metal cladding.
 Overglazing of Nuplex high build coating systems.
 Particularly recommended for the upgrading of buildings which have been previously coated (that are in sound condition) and generally require a change of colour or upgrading.

No warranty either expressed or implied or statutory is made by NUPLEX in this document except as expressly stated in any sale and purchase agreement entered into between NUPLEX and the buyer.

This document is a technical data information sheet. The description of the product or products and the properties of the product or products contained in this document is for the sole purpose of identifying the product or products and describing their property or properties and does not constitute a warranty that the product or its properties shall conform to that description; nor is the description of the product and/or its properties a warranty by NUPLEX that the goods are suitable for a particular purpose.

NUPLEX CONSTRUCTION PRODUCTS

PO Box 12841, Penrose, Auckland Telephone 0-9-579 2029 Fax 0-9-579 3709 www.nuplexconstruction.co.nz email: bpdsales@nuplex.co.nz

H A M I L T O N	PALMERSTON NORTH	W E L L I N G T O N	CHRISTCHURCH
Telephone 0-7-847 8658	Telephone 0-6-353 3685	Telephone 0-4-477 7040	Telephone 0-3-366 6802
Fax 0-7-847 3766	Fax 0-6-353 3632	Fax 0-4-477 7039	Fax 0-3-379 0279

FLEXIGLAZE (cont'd)**NOT****RECOMMENDED:**

- Continuous immersion.
- Areas subjected to chemical or physical attack.
- As a weatherproofing coating on its own.
- Not tested to EM4 on Fibrecement.

APPLICATION**METHOD:**

Brush, roller, conventional or airless spray.

COVERAGE RATES:

Smooth surfaces: 8-10m²/litre

Rough surfaces: 6-8m²/litre

Number of coats: 2 recommended

One coat is recommended where a Nuplex high build coating system is being overglazed and a colour change is not envisaged (i.e. base coat and glaze are the same colour).

FILM BUILD (TOTAL):
(2 coats)

Wet: 200 microns

Dry: 80 microns

THINNING:

Clean potable water, but not recommended.

DRY TIMES:

(20°C 50% RH)

Touch dry: 2 hours

Recoat: 3 hours

Overglaze: 24 hours

CLEAN UP:

Water

CAUTION:

Provide adequate ventilation when spraying in confined areas.

SHELF LIFE:

24 months in unopened containers.

PACKAGING:

10 litre polypails

FLASH POINT:

None

**NZ DANGEROUS
GOODS CLASS:**

Not applicable