



| MANUAL SECTION | ISSUE DATE | AUTHORISED | REPLACES | PAGE |
|-----------------|------------------|------------|-----------------|---------------|
| <i>Sundries</i> | <i>July 1993</i> | <i>PM</i> | <i>Sep 1990</i> | <i>1 of 2</i> |

SITUGLAZE

DESCRIPTION

Solution Acrylic

PROPERTIES / FEATURES:

- SITUGLAZE is a solution acrylic glaze which is especially recommended for use in heavy wear and industrial areas, i.e. Commercial Kitchens.
 - Non-yellowing.
 - Good exterior durability.
 - Good flexibility.
 - Excellent soiling resistance.
- Total Solids Content: 18%
 Volume Solids: 15%
 SG: 0.9 Kg/litre
 Colour: clear liquid
 Finish: full gloss
 Solvent: Xylene / Toluene
 Minimum application temperature: + 10°C

SUGGESTED USES:

- Interior glaze for Situflex high build acrylic wall coatings.
- Exterior glaze for selected high build coatings.
- Reglazing concrete roof tiles.
- Glazing exposed aggregate.

NOT RECOMMENDED:

- Areas subjected to chemical attack.
- Continuous immersion.
- Application to damp surfaces.

APPLICATION

METHOD:

Airless and conventional spray.

COVERAGE RATE:

6m² / litre (approx) one coat.
 Number of coats - 1 or 2

No warranty either expressed or implied or statutory is made by NUPLEX in this document except as expressly stated in any sale and purchase agreement entered into between NUPLEX and the buyer.

This document is a technical data information sheet. The description of the product or products and the properties of the product or products contained in this document is for the sole purpose of identifying the product or products and describing their property or properties and does not constitute a warranty that the product or its properties shall conform to that description; nor is the description of the product and/or its properties a warranty by NUPLEX that the goods are suitable for a particular purpose.

NUPLEX CONSTRUCTION PRODUCTS

PO Box 1 2841, Penrose, Auckland Telephone 0-9-579 2029 Fax 0-9-525 3709 www.nuplexbuilding.co.nz email: bpdsales@nuplex.co.nz

| | | | |
|------------------------|-------------------------------|------------------------|-------------------------|
| H A M I L T O N | P A L M E R S T O N N O R T H | W E L L I N G T O N | C H R I S T C H U R C H |
| Telephone 0-7-847 8658 | Telephone 0-6-353 3685 | Telephone 0-4-499 1341 | Telephone 0-3-366 6802 |
| Fax 0-7-847 3766 | Fax 0-6-353 3632 | Fax 0-4-471 5709 | Fax 0-3-365 7845 |

FILM BUILD:

- Wet: 166 microns (.006")
- Dry: 25 microns (.001")

THINNING

Xylene, although not recommended.

DRY TIMES:
(20°C 50% RH)

Touch Dry: 30 minutes
Recoat: 2 hours

CLEAN UP

Nuplex UNIVERSAL CLEANING SOLVENT

CAUTION

- Wear protective equipment.
- Ensure MSDS sheets are available on site.
- Contents flammable.

SHELF LIFE:

12 months in unopened containers.

PACKAGING

20 litre screw cap cans.

FLASH POINT:

+ 10°C

NZ DANGEROUS
GOODS CLASS

3a

IMCO Class 3.2
UN No. 1866
IMDG code
Page number 3105