

MANUALSECTION

ISSUE DATE

AUTHORISED

REPLACES

PAGE

Sundries

August 1997

July 1993

SURFAPATCH

GENERIC TYPE

Latex modified cementitious patching compound.

PROPERTIES/FEATURES

SURFAPATCH is a 2 pack patching compound consisting of a premixed cementitious powder and a latex binder.

Excellent adhesion to a wide variety of substrates.

Tough and durable.

Good impact resistance.

Can be feathered to a fine edge.

May be overcoated with most types of coatings.

May be applied to damp surfaces.

Minimum application temperature - + 10°C

Colour - Grey

Finish - Similar to concrete plaster

SUGGESTED USES

For patching and flushing interior/exterior fairfaced and precast concrete, fibre cement sheeting, timber sheeting etc.

NOT RECOMMENDED

Application to active joints and cracks.

Any single application exceeding 2mm film build.

Any single application with the addition of silica sand exceeding 5mm film build.

...12

No warranty either expressed or implied or statutory is made by NUPLEX in this document except as expressly stated in any sale and purchase agreement entered into between NUPLEX and the buyer.

This document is a technical data information sheet. The description of the product or products and the properties of the product or products contained in this document is for the sole purpose of identifying the product or products and describing their property or properties and does not constitute a warranty that the product or its properties shall conform to that description; nor is the description of the product and/or its properties a warranty by NUPLEX that the goods are suitable for a particular purpose.

NUPLEX CONSTRUCTION PRODUCTS

POBox 12841, Penrose, Auckland Telephone 0-9-5792029 Fax 0-9-5253709 www.nuplexbuilding.co.nz email: bpdsales@nuplex.co.nz

H A M I L T O N
Telephone 0-7-847 8658
Fax 0-7-847 3766

PALMERSTON NORTH
Telephone 0-6-353 3685
Fax 0-6-353 3632

W E L L I N G T O N
Telephone 0-4-499 1341
Fax 0-4-471 5709

C H R I S T C H U R C H
Telephone 0-3-366 6802
Fax 0-3-365 7845

SURFAPATCH (cont'd)

MIX RATIO

Volume - 3 parts powder : 1 part liquid
Weight - 3 parts powder : 1 part liquid

APPLICATION METHOD

Trowel, broadknife, etc.

COVERAGE RATES

1 unit has volume capacity of 9 litres.

FILM BUILD

Any single application must not exceed 2mm; 5mm if silica sand is added.
Allow to dry between coats.

THINNING

Consistency may be varied by altering the mix ratio of liquid to powder.

DRY TIMES

Touch dry	6 hours
Hard dry	48 hours
Cure	28 days
Recoat	6 hours
Coating/Paint (water based)	12 hours
Coating/Paint (solvent)	48 hours

CLEAN UP

Water.

SHELF LIFE

12 months if stored in original unopened containers in a dry place.

PACKAGING

4 litres liquid.
1 2 kgs powder.

FLASH POINT

None.

NZ DANGEROUS GOODS CLASS

Not applicable.