

MANUAL SECTION	ISSUE DATE	AUTHORISED	REPLACES	PAGE
----------------	------------	------------	----------	------

<i>Interior/Exterior</i>	<i>Sept 2006</i>	<i>PM</i>	<i>June 1993</i>	<i>1 of 2</i>
--------------------------	------------------	-----------	------------------	---------------

SURFAGLAZE TOPCOAT

GENERIC TYPE:

A 2 pack acrylic urethane enamel.

TYPICAL PROPERTIES / FEATURES:

- Surfaglaze Topcoat is an aliphatic urethane modified acrylic coating available in clear and pigmented form.
- Excellent toughness and resilience.
- Non-yellowing.
- Good re-coatability.
- Good chemical resistance.
- Excellent colour fastness and UV stability.
- Contains sophisticated UV protective additives.
- Finish: Full Gloss
Semi Gloss to order
- Colour: Refer Nuplex Colour and Texture Guide
- Type of Urethane: Aliphatic
- Minimum application temperature +10°C.
- Solvent: Xylene/propylene glycol monomethyl ether acetate
- Volume Solids: 40%. TSC: Clear 48%. Pigmented 58%
- Moisture Vapour (BS 3177:1959) – 36 gms permeability: mil/m²/24 hours
- Weathering: (1000 hrs QUV accelerated weather tester to ASTM G-53-77. 4 hours UV 60°C, 4 hours condensation 40°C).
No visible effect.

SUGGESTED USES:

- With or without Surfaglaze Basecoat.
- Interior/Exterior application.
- A long life protective coating for areas subjected to: severe UV attack, pollution, moderate chemical contamination.
- Glaze/top coating for high build Surfaglaze system. Refer data sheets Surfaglaze High Build Systems.
- Traffic coating for specialised flooring systems.
- The coating of roofs constructed of fibre cement sheeting, clay, metal and concrete tiles.
- **Hygienic Metal protection coating** over steel or anti-corrosive coatings. The high gloss finish is hard and durable.

No warranty either expressed or implied or statutory is made by NUPLEX in this document except as expressly stated in any sale and purchase agreement entered into between NUPLEX and the buyer. CERTIFIED ISO 9001 REG. NO. 158
This document is a technical data information sheet. The description of the product or products and the properties of the product or products contained in this document is for the sole purpose of identifying the product or products and describing their property or properties and does not constitute a warranty that the product or its properties shall conform to that description; nor is the description of the product and/or its properties a warranty by NUPLEX that the goods are suitable for a particular purpose.

NUPLEX CONSTRUCTION PRODUCTS **WWW.NUPLEXCONSTRUCTION.CO.NZ**

PO Box 1 2841, Penrose, Auckland Telephone: 0-9-579 2029, Fax: 0-9-525 3709, Email: bpdsales@nuplex.co.nz

H A M I L T O N	P A L M E R S T O N	N O R T H	W E L L I N G T O N	C H R I S T C H U R C H
Telephone: 0-7-847 8658	Telephone: 0-6-353 3685		Telephone: 0-4-477 7040	Telephone: 0-3-366 6802
Fax: 0-7-847 3766	Fax: 0-6-353 3632		Fax: 0-4-477 7039	Fax: 0-3-379 0279

NOT RECOMMENDED: • Prolonged contact with strong acids, alkalies or aggressive solvents.

• Application to damp substrates or during damp humid conditions.

APPLICATION:

Method: Brush, roller (small areas only), airless and conventional spray.

Mix Ratios: Volume – 7:1 (A:B). Pot Life: 2hrs

Mixing: Thoroughly mix Part A and Part B in the correct proportions then allow to stand 10-15 minutes before use.

Coverage Rates:

Walls	6m ² /litre/coat
Floors	4m ² /litre/coat

WET FILM BUILD:

(Theoretical)

Walls: 165 microns (0.0066”) per coat

Floors: 250 microns (0.010”) per coat

DRY FILM BUILD:

(Theoretical)

Walls: 66 microns (0.026”) per coat

Floors: 100 microns (0.0040”) per coat

NO. OF COATS:

Walls: 1 – 2

Floors: 2 minimum

Metal protection: 2

THINNING:

Thin to application viscosity using Surfaglaze thinners.

DRY TIMES:

Tack Free: 1 hour. Re-coat 4 hours. Hard Dry 12 hours

Note: With spray application, a wet-on technique can be used.

CLEAN UP:

- Nuplex Universal Cleaning Solvent
- Surfaglaze Thinners

CAUTION:

- Part B contains reactive Isocyanate.
- When spraying, wear protective clothing, gloves and eye and face protection, including suitable breathing protection such as an air supplied respirator or hood.
- Do not breathe vapour or spray.
- Shelf life: 24 months in un-opened tins